

GARDAPAT 13

KIARA

TECHNICAL DATA

Property	Test Method	Unit	Tolerance	90	100	115	135	150	200	250
Substance	ISO 536 TAPPI T410	g/m ²	±4%	90	100	115	135	150	200	250
Thickness	ISO 534 TAPPI T411	µm	±4%	117	130	149	175	195	260	325
Thickness (pt.)	ISO 534 TAPPI T411	pt.	±4%	4.6	5.1	5.9	6.9	7.68	10.2	12.8
Bulk	ISO 534 TAPPI T411	cm ³ /g	-	1.30	1.30	1.30	1.30	1.30	1.30	1.30
Opacity	ISO 2471 TAPPI T519	%	-2.0	91.5	93.0	95.0	96.0	97.5	98.0	99.0
Whiteness D65/10°	ISO 11475	CIE	±3	88	88	88	88	88	88	88
Relative humidity	TAPPI T502	%	±7	50	50	50	50	50	50	50

Production methods are based on the specified official standards but may differ in certain details. The provided data has been agreed upon in good faith and tested to the best of our knowledge; however, we cannot guarantee the results of any subsequent processing beyond our control. We strongly recommend that clients evaluate whether our paper meets their specific requirements and the standards of their final products



The mark of
responsible forestry
FSC® C007915